

CERTIGRADE[®] **Rebutted/Rejointed Shingles**

CERTIGROOVE[®] **Machine Grooved Shakes**



These products are manufactured specifically for exterior and interior wall surface uses. They are a low maintenance product that adds beauty, texture, durability and insulating qualities to either new construction or remodelling and renovation of existing structures.

Cedar
Shake
& Shingle
Bureau



Richard Lawson, Architect

Beautiful Durable Insulative Wind Resistant Withstands Thermal Shock Impact Resistant Light Weight

CERTIGROOVE[®]

Machine Grooved Shakes

Appearance: Machine grooved for a shake texture from Number 1 Grade Blue Label CERTIGRADE red cedar shingles, trimmed for parallel edges with butts sawn at right angles.
Finishes: Natural, primed white, primed gray, or special order colors.
Lengths: 16-inch, 18-inch and 24-inch.

NUMBER 1 GRADE, BLUE LABEL

Description — Lengths 16-inch, 18-inch, 24-inch; width 14" maximum, 4" minimum; thickness of 16-inch is 5/2" (5 butts together measures 2" thick), 18-inch is 5/2-1/4" thick, 24-inch is 4/2" thick. Clear heartwood: 100% edge grain; no defects.

Recommended Use — For exterior and interior walls where a premium quality product is desired.

Wall Exposure Table

Shingle Length	Max. Weather Exposure	
	Single Course	Double Course
16"	7"	12"
18"	8"	14"
24"	10 1/2"	16"

CERTIGRADE[®]

Rebuted/Rejointed Shingles

Appearance: Manufactured from Number 1 Grade Blue Label and Number 2 Grade Red label CERTIGRADE red cedar shingles, trimmed for parallel edges with butts sawn at right angles. Available in both sawn and sanded face textures.
Finishes: Natural, primed white, primed gray, or special order colors.
Lengths: 16-inch, 18-inch and 24-inch.

NUMBER 1 GRADE, BLUE LABEL

Description — Lengths 16-inch, 18-inch, 24-inch; width 14" maximum, 4" minimum; thickness of 16-inch is 5/2" (5 butts together measures 2" thick), 18-inch is 5/2-1/4" thick, 24-inch is 4/2" thick. Clear heartwood: 100% edge grain; no defects.

Recommended Use — For exterior and interior walls where a premium quality product is desired.

NUMBER 2 GRADE, RED LABEL

Description — Lengths 16-inch, 18-inch, 24-inch; thickness of 16-inch is 5/2" (5 butts together measures 2" thick), 18-inch is 5/2-1/4" thick, 24-inch is 4/2" thick. Width 14" maximum, 4" minimum. Face must be 10", 11" and 16" clear or better on 16-inch, 18-inch and 24-inch shingles, respectively. Limited sapwood and flat grain are allowed. Limited knots and defects are allowed above the clear portion.

Recommended Use — For exterior and interior walls where a good quality product is desired.

Wall Exposure Table — No. 1 Grade, Blue Label*

Shingle Length	Max. Weather Exposure	
	Single Course	Double Course
16"	7"	12"
18"	8"	14"
24"	10 1/2"	16"

* Maximum weather exposure for No. 2 Grade, Red label Rebuted and Rejointed shingles should be in accordance with the manufacturer's recommendations.

- These red cedar shakes and shingles are manufactured in accordance with standards established by the Cedar Shake & Shingle Bureau.
- This is only a product description sheet necessary for selection of materials and grades. For a new roof construction manual and/or wall manual please contact:



US Address
P.O. Box 1178
Sumas, WA 98295 - 1178

Tel: (604) 820-7700
Fax: (604) 820-0266
www.cedarbureau.org

Canadian Address
#2 - 7101 Horne Street
Mission, B.C. V2V 7A2